



PUD 308

Waterborne polyurethane dispersion

PRODUCT DESCRIPTION

PUD 308 is an aqueous aliphatic polyurethane dispersion

CHARACTERISTIC

at the contract of				
Chemical Structure	Waterhorne	anionic	nolvester-hased	l polyurethane dispersion

Appearance Milky Liquid

Reference method

Non-volatile content	%	40±2	ASTM D2369-07
(by weight % (105°C))			

pH (23°C) 8±1 ISO 976

Viscosity (23°C) cps <2000

Spindle R3

FILM PROPERTIES

			Reference Method
100% Modulus	N/mm²	2	ASTM D1708-18
Elongation at break	%	>1000	ASTM D1708-18
Tensile strength	N/mm²	18	ASTM D1708-18
MFFT	°C	<0	ASTM D2354
Light Fastness	Five scale	5/5	EN ISO 105-B02

Films are dried at room temperature

Head office Denge Kimya ve Tekstil San. Tic A.S-Velimese OSB Mah 259 No:4-1 Ergene /Tekirdag Phone +902826745400
The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. Our recommendations are in line with our present state of knowledge and do not provide any guarantee.





PUD 308

Waterborne polyurethane dispersion

KEY PROPERTIES

• Very flexible additive to paint formulation.

APPLICATIONS

- PUD 308 can be diluted with water.
- It can be formulated with crosslinkers, pigments, thickeners, and other additives
- Suitable for mechanical foaming and coating applications
 - Mix well before use.

PACKAGING & STORAGE

Packaging type

120 kg plastic drums, 1000 kg IBC's.

Storage



In originally closed containers' dispersions are stable when stored at 10°C-30°C for 6 months. The containers must be well closed to prevent the evaporation of water which may result in the formation of a non-redispersible film. The recommended temperature-range for storage is freezing or storage at higher temperatures than 30°C can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi, or algae can damage the product irreversibly. A longer storage than six months does not mean that the product is not usable anymore, but we recommend to checking the specification data before use.

Head office Denge Kimya ve Tekstil San. Tic A.S-Velimese OSB Mah 259 No:4-1 Ergene /Tekirdag Phone +902826745400
The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. Our recommendations are in line with our present state of knowledge and do not provide any guarantee.